

AMENDMENTS TO THE ABSTRACT:

Please amend the ABSTRACT as follows:

ABSTRACT

Key actuators and other switching devices are formed of a conductive loaded resin-based material. The conductive loaded resin-based material comprises micron conductive powder(s), conductive fiber(s), or a combination of conductive powder and conductive fibers in a base resin host. The ratio of the weight of the conductive powder(s), conductive fiber(s), or a combination of conductive powder and conductive fibers to the weight of the base resin host is between about 0.20 and 0.40. The micron conductive powders are formed from non-metals, such as carbon, graphite, that may also be metallic plated, or the like, or from metals such as stainless steel, nickel, copper, silver, that may also be metallic plated, or the like, or from a combination of non-metal, plated, or in combination with, metal powders. The micron conductor fibers preferably are of nickel plated carbon fiber, stainless steel fiber, copper fiber, silver fiber, or the like. ~~The conductive loaded resin-based key actuators and other switching devices can be formed using methods such as injection molding compression molding or~~

INT-03-010

~~extrusion. The conductive loaded resin-based material used to form the key actuators and other switching devices can also be in the form of a thin flexible woven fabric that can readily be cut to the desired shape.~~